

Kriebstein Performance Fiber®



TYPICAL END USES

graphic papers

TECHNICAL DATASHEET

Tolerances

Brightness	ISO 2470	%	70	± 3
Ash content	DIN 54370	%	14	± 5
Freeness	ISO 5276-2	ml CSF	140	± 20
Tensile Index	DIN ISO 1924-2	Nm/g	29	± 2
Solid Content	DIN EN ISO 287	%	40	± 2

ENVIRONMENT

Renewable fibre
Recyclable fibers
Sustainable sources
no chlorine bleaching in process

CERTIFICATES

FSC®
PEFC™

Kübler & Niethammer Papierfabrik Kriebstein AG
Bauhofstraße 1
OT Kriebethal, 09648 Kriebstein
Tel +49 (0) 34327 97-50
info@k-n-paper.de